



Bloomington Specialty Products  
 1100 N Oard Road  
 Bloomington, IN 47404  
 812-333-8560

07/11/2024

### 4003-Rock Dust

Procedure	Sieve/Test	Average	Unit	Rock Dust
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#20 (.85mm)	100	%	100-100
	#30 (.6mm)	100	%	
	#60 (.25mm)	100	%	
	#80 (.18mm)	99	%	
	#100 (.15mm)	98	%	
	#140 (.106mm)	92	%	
	#200 (75µm)	84	%	70-100
	#325 (45µm)	72	%	
	Al2O3	0.03		
	CaCO3	96.67		
	Fe2O3	0.16		
	MgCO3	1.01		
	SiO2	0.57		0.00-4.00

Name/Title      Laresa Ingram / IND QC Manager