



Bloomington Specialty Products
 1100 N Oard Road
 Bloomington, IN 47404
 812-333-8560

05/01/2025

QA #16 Mineral Filler-4003

Procedure	Sieve/Test	Average	Unit	QA #16 Mineral Filler
	#8 (2.36mm)	100.0	%	100-100
	#16 (1.18mm)	100.0	%	100-100
	#30 (.6mm)	100.0	%	100-100
	#60 (.25mm)	99.9	%	
	#80 (.18mm)	99.4	%	
	#100 (.15mm)	98.4	%	96-100
	#140 (.106mm)	94.0	%	80-100
	#200 (75µm)	86.7	%	70-100
	#325 (45µm)	76.1	%	25-100
	Al2O3	0.10	%	
	CaCO3	96.70	%	
	Calcium (Ca)	38.65	%	
	Fe2O3	0.18	%	
	Magnesium (Mg)	0.62	%	
	MgCO3	2.00	%	
	SiO2	0.82	%	0.00-4.00

This report certifies tickets issued to the listed customer for 24 hours after 6:00AM EST of the date published. If the COA was issued on a Saturday, it certifies tickets until Tuesday at 5:59AM EST. (If a Monday holiday, COA issued Saturday certifies until Wednesday at 5:59AM EST)

Name/Title

Laresa Ingram / QC Manager