



Bloomington Specialty Products
1100 N Oard Road
Bloomington, IN 47404
812-333-8560

09/02/2025

4003-Rock Dust

Procedure	Sieve/Test	Average	Unit	Rock Dust
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#20 (.85mm)	100	%	100-100
	#30 (.6mm)	100	%	
	#60 (.25mm)	99	%	
	#80 (.18mm)	98	%	
	#100 (.15mm)	97	%	
	#140 (.106mm)	92	%	
	#200 (75µm)	84	%	70-100
	#325 (45µm)	77	%	
	Al ₂ O ₃	0.09	%	
	CaCO ₃	95.80	%	
	Calcium (Ca)	38.36	%	
	Fe ₂ O ₃	0.19	%	
	Magnesium (Mg)	0.55	%	
	MgCO ₃	2.15	%	
	SiO ₂	0.68	%	0.00-4.00

Name/Title

Laresa Ingram / QC Manager