



12/01/2025

4000-#1 BSP

Procedure	Sieve/Test	Average	Unit	#1 BSP
	1/4" (6.3mm)	100	%	100-100
	#4 (4.75mm)	100	%	90-100
	#6 (3.35mm)	72	%	
	#8 (2.36mm)	35	%	
	#12 (1.7mm)	14	%	
	#16 (1.18mm)	3	%	0-20
	#30 (.6mm)	2	%	
	#50 (.3mm)	2	%	
	#80 (.18mm)	1	%	
	#100 (.15mm)	1	%	
	Al2O3	0.10	%	
	CaCO3	94.58	%	94.50-100.00
	Calcium (Ca)	37.85	%	
	Fe2O3	0.16	%	
	Magnesium (Mg)	0.74	%	
	MgCO3	2.67	%	0.00-2.80
	SiO2	0.93	%	

This report certifies tickets issued to the listed customer for 24 hours after 6:00AM EST of the date publised. If the COA was issued on a Saturday, it certifies ticket until Tuesday at 5:59AM EST, or Wednesday at 5:59AM EST in the case of a Monday holiday.

Name/Title

Laresa Ingram / QC Manager