



Bloomington Specialty Products
1100 N Oard Road
Bloomington, IN 47404
812-333-8560

12/01/2025

4003-QA #16 Mineral Filler

Procedure	Sieve/Test	Average	Unit	QA #16 Mineral Filler
	#8 (2.36mm)	100.0	%	100-100
	#16 (1.18mm)	100.0	%	100-100
	#30 (.6mm)	100.0	%	100-100
	#60 (.25mm)	99.8	%	
	#80 (.18mm)	99.2	%	
	#100 (.15mm)	98.3	%	96-100
	#140 (.106mm)	94.2	%	80-100
	#200 (75µm)	86.9	%	70-100
	#325 (45µm)	81.3	%	25-100
	Al ₂ O ₃	0.10	%	
	CaCO ₃	95.37	%	
	Calcium (Ca)	37.30	%	
	Fe ₂ O ₃	0.18	%	
	Magnesium (Mg)	1.10	%	
	MgCO ₃	2.49	%	
	SiO ₂	0.82	%	0.00-4.00

This report certifies tickets issued to the listed customer for 24 hours after 6:00AM EST of the date published. If the COA was issued on a Saturday, it certifies tickets until Tuesday at 5:59AM EST. (If a Monday holiday, COA issued Saturday certifies until Wednesday at 5:59AM EST)

Name/Title

Laresa Ingram / QC Manager