



Bloomington Specialty Products  
1100 N Oard Road  
Bloomington, IN 47404  
812-333-8560

12/01/2025

### 4003-Rock Dust

| Procedure | Sieve/Test                     | Average | Unit | Rock Dust |
|-----------|--------------------------------|---------|------|-----------|
|           | #8 (2.36mm)                    | 100     | %    |           |
|           | #16 (1.18mm)                   | 100     | %    |           |
|           | #20 (.85mm)                    | 100     | %    | 100-100   |
|           | #30 (.6mm)                     | 100     | %    |           |
|           | #60 (.25mm)                    | 100     | %    |           |
|           | #80 (.18mm)                    | 99      | %    |           |
|           | #100 (.15mm)                   | 98      | %    |           |
|           | #140 (.106mm)                  | 92      | %    |           |
|           | #200 (75µm)                    | 85      | %    | 70-100    |
|           | #325 (45µm)                    | 77      | %    |           |
|           | Al <sub>2</sub> O <sub>3</sub> | 0.10    | %    |           |
|           | CaCO <sub>3</sub>              | 95.39   | %    |           |
|           | Calcium (Ca)                   | 37.11   | %    |           |
|           | Fe <sub>2</sub> O <sub>3</sub> | 0.18    | %    |           |
|           | Magnesium (Mg)                 | 1.47    | %    |           |
|           | MgCO <sub>3</sub>              | 2.50    | %    |           |
|           | SiO <sub>2</sub>               | 0.71    | %    | 0.00-4.00 |

Name/Title

Laresa Ingram / QC Manager