



Bloomington Specialty Products
 1100 N Oard Road
 Bloomington, IN 47404
 812-333-8560

03/02/2026

4001-#2 BSP

Procedure	Sieve/Test	Average	Unit	#2 BSP
	#8 (2.36mm)	100	%	99.5-100
	#12 (1.7mm)	100	%	98-100
	#16 (1.18mm)	91	%	75-95
	#20 (.85mm)	61	%	40-70
	#30 (.6mm)	20	%	10-60
	#50 (.3mm)	3	%	
	#80 (.18mm)	2	%	
	#100 (.15mm)	2	%	0-7
	Al2O3	0.10	%	
	CaCO3	95.27	%	82.00-100.00
	Calcium (Ca)	38.15	%	
	Fe2O3	0.16	%	0.00-0.24
	Magnesium (Mg)	0.56	%	
	MgCO3	1.99	%	0.00-2.50
	SiO2	0.91	%	0.00-2.50
	Grad Loss	0.030	%	

This report certifies tickets issued to the listed customer for 24 hours after 6:00AM EST of the date published. If the COA was issued on a Saturday, it certifies ticket until Tuesday at 5:59AM EST, or Wednesday at 5:59AM EST in the case of a Monday holiday.

Name/Title Laresa Ingram / QC Manager