



Bloomington Specialty Products
 1100 N Oard Road
 Bloomington, IN 47404
 812-333-8560

06/01/2026

4000-#1 BSP

Procedure	Sieve/Test	Average	Unit	#1 BSP
	1/4" (6.3mm)	100	%	100-100
	#4 (4.75mm)	100	%	90-100
	#6 (3.35mm)	78	%	
	#8 (2.36mm)	42	%	
	#12 (1.7mm)	16	%	
	#16 (1.18mm)	3	%	0-20
	#30 (.6mm)	2	%	
	#50 (.3mm)	2	%	
	#80 (.18mm)	1	%	
	#100 (.15mm)	1	%	
<hr/>				
	Al2O3	0.11	%	
	CaCO3	95.38	%	82.00-100.00
	Calcium (Ca)	38.17	%	
	Fe2O3	0.17	%	
	Magnesium (Mg)	0.60	%	
	MgCO3	2.19	%	0.00-2.80
	SiO2	1.02	%	
	Grad Loss	0.012	%	

This report certifies tickets issued to the listed customer for 24 hours after 6:00AM EST of the date published. If the COA was issued on a Saturday, it certifies ticket until Tuesday at 5:59AM EST, or Wednesday at 5:59AM EST in the case of a Monday holiday.

Name/Title Laresa Ingram / QC Manager