



Bloomington Specialty Products  
 1100 N Oard Road  
 Bloomington, IN 47404  
 812-333-8560

06/01/2026

**4003-QA #16 Mineral Filler**

Procedure	Sieve/Test	Average	Unit	QA #16 Mineral Filler
	#8 (2.36mm)	100.0	%	100-100
	#16 (1.18mm)	100.0	%	100-100
	#30 (.6mm)	100.0	%	100-100
	#60 (.25mm)	99.7	%	
	#80 (.18mm)	99.0	%	
	#100 (.15mm)	98.0	%	96-100
	#140 (.106mm)	93.4	%	80-100
	#200 (75µm)	86.2	%	70-100
	#325 (45µm)	77.0	%	25-100
	Al2O3	0.12	%	
	CaCO3	96.23	%	
	Fe2O3	0.19	%	
	MgCO3	1.99	%	
	SiO2	0.92	%	0.00-4.00
	-#200 (75um)	77.0	%	
	Grad Loss	0.016	%	
	Wash Loss (#200/75um)	70.2	%	

This report certifies tickets issued to the listed customer for 24 hours after 6:00AM EST of the date published. If the COA was issued on a Saturday, it certifies tickets until Tuesday at 5:59AM EST. (If a Monday holiday, COA issued Saturday certifies until Wednesday at 5:59AM EST)

Name/Title

Laresa Ingram / QC Manager