



Bloomington Specialty Products
 1100 N Oard Road
 Bloomington, IN 47404
 812-333-8560

06/01/2026

4003-Rock Dust

Procedure	Sieve/Test	Average	Unit	Rock Dust
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#20 (.85mm)	100	%	100-100
	#30 (.6mm)	100	%	
	#60 (.25mm)	99	%	
	#80 (.18mm)	98	%	
	#100 (.15mm)	96	%	
	#140 (.106mm)	91	%	
	#200 (75µm)	83	%	70-100
	#325 (45µm)	73	%	
	Al2O3	0.12	%	
	CaCO3	96.22	%	
	Fe2O3	0.19	%	
	MgCO3	1.99	%	
	SiO2	0.92	%	0.00-4.00

Name/Title Laresa Ingram / QC Manager