



Bloomington Specialty Products
1100 N Oard Road
Bloomington, IN 47404
812-333-8560

08/03/2026

4003-Rock Dust

Procedure	Sieve/Test	Average	Unit	Rock Dust
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#20 (.85mm)	100	%	100-100
	#30 (.6mm)	100	%	
	#60 (.25mm)	100	%	
	#80 (.18mm)	99	%	
	#100 (.15mm)	98	%	
	#140 (.106mm)	93	%	
	#200 (75µm)	87	%	70-100
	#325 (45µm)	77	%	
	Al ₂ O ₃	0.18	%	
	CaCO ₃	96.42	%	
	Calcium (Ca)	38.62	%	
	Fe ₂ O ₃	0.17	%	
	Magnesium (Mg)	0.57	%	
	MgCO ₃	1.84	%	
	SiO ₂	1.03	%	0.00-4.00

Name/Title

Laresa Ingram / QC Manager