



Bloomington Specialty Products
1100 N Oard Road
Bloomington, IN 47404
812-333-8560

09/02/2026

4001-#2 BSP

Procedure	Sieve/Test	Average	Unit	#2 BSP
	#8 (2.36mm)	100	%	99.5-100
	#12 (1.7mm)	100	%	98-100
	#16 (1.18mm)	93	%	75-95
	#20 (.85mm)	63	%	40-70
	#30 (.6mm)	25	%	10-60
	#50 (.3mm)	4	%	
	#80 (.18mm)	2	%	
	#100 (.15mm)	2	%	0-7
	Al ₂ O ₃	0.10	%	
	CaCO ₃	96.40	%	82.00-100.00
	Calcium (Ca)	38.60	%	
	Fe ₂ O ₃	0.16	%	0.00-0.24
	Magnesium (Mg)	0.52	%	
	MgCO ₃	1.80	%	0.00-2.50
	SiO ₂	0.94	%	0.00-2.50
	Grad Loss	0.036	%	

This report certifies tickets issued to the listed customer for 24 hours after 6:00AM EST of the date published. If the COA was issued on a Saturday, it certifies ticket until Tuesday at 5:59AM EST, or Wednesday at 5:59AM EST in the case of a Monday holiday.

Name/Title

Laresa Ingram / QC Manager